

DOW CORNING CORP. -- 282 ADHESIVE -- 8040-00-148-9737

===== Product Identification =====

Product ID:282 ADHESIVE

MSDS Date:01/01/1985

FSC:8040

NIIN:00-148-9737

MSDS Number: BDCMR

=== Responsible Party ===

Company Name:DOW CORNING CORP.

Address:3901 SOUTH SAGINAW ROAD

Box:997

City:MIDLAND

State:MI

ZIP:48640

Country:US

Info Phone Num:517-496-5900

Emergency Phone Num:517-496-5900

CAGE:5D028

=== Cont

ractor Identification ===

Company Name:DOW CORNING CORP

Address:3901 S SAGINAW RD

Box:997

City:MIDLAND

State:MI

ZIP:48686-0997

Country:US

Phone:517-496-6000/517-496-6315

CAGE:5D028

Company Name:DOW CORNING CORP

Address:2200 W SALZBURG RD

Box:City:AUBURN

State:MI

ZIP:48611

Country:US

Phone:517-496-4388

CAGE:71984

===== Composition/Information on Ingredients =====

Ingred Name:XYLENES (O-,M-,P- ISOMERS) (SARA III)

CAS:1330-20-7

RTECS #:ZE2100000

Fraction by Wt: 40%

OSHA PEL:100

PPM/150 STEL  
ACGIH TLV:100 PPM/150STEL;9192  
EPA Rpt Qty:1000 LBS  
DOT Rpt Qty:1000 LBS

=====  
Hazards Identification  
=====

Effects of Overexposure:IRRITATES SKIN & EYES.MAY CAUSE SLIGHT ANESTHESIA,HEADACHES,ETC.

=====  
First Aid Measures  
=====

First Aid:FLUSH WITH WATER.INHALATION-REMOVE TO FRESH AIR.OBTAIN MEDICAL ATTENTION.

=====  
Fire Fighting Measures  
=====

Flash Point:80F,26C

CC

Lower Limits:1.0

Upper Limits:7.0

Extinguishing Media:CO\*2 OR FOAM

Fire Fighting Procedures:SELF-CONTAINED BREATHING APPARATUS & PROTECTIVE CLOTHING WRN

Unusual Fire/Explosion Hazard:NONE

=====  
Accidental Release Measures  
=====

Spill Release Procedures:USE ABSORBENT MATERIAL TO COLLECT AND CONTAIN FOR SALVAGE OR DISPOSAL

=====  
Handling and Storage  
=====

Handling and Storage Precautions:PRODUCT IS FLAMMABLE.USE REASONABLE CARE.

Other Precautions:NONE

=====  
Exposure Controls/Personal Protection  
=====

Respiratory Protection:ORGANIC VAPOR TYPE

Ventilation:GENERAL-MECHANICAL RECOMMENDED

Protective Gloves:RUBBER OR PLAST

Eye Protection:SAFETY GLASSES

Supplemental Safety and Health

=====  
Physical/Chemical Properties  
=====

HCC:F3

Boiling Pt.=143.3C, 290.F

Vapor Pres:10

Vapor Density:>1.0

Spec Gravity:0.9

Evaporation Rate & Reference: