

DEXTER CORP,HYSOL DIV. -- EA 901 PART A -- 8040-00-831-3403

=====
Product Identification
=====

Product ID:EA 901 PART A

MSDS Date:01/01/1985

FSC:8040

NIIN:00-831-3403

Kit Part:Y

MSDS Number: BFRQJ

=== Responsible Party ===

Company Name:DEXTER CORP,HYSOL DIV.

Emergency Phone Num:415-687-4201

CAGE:1JB33

=== Contractor Identification ===

Company Name:DEXTER CORP THE HYSOL DIV

Address:1 DEXTER DR

Box

:City:SEABROOK

State:NH

ZIP:03874

Country:US

Phone:603-474-5541/FAX: 603-474-5545

CAGE:1JB33

Company Name:DEXTER CORPORATION ADHESIVE & COATING SYSTEMS

Address:2850 WILLOW PASS ROAD

Box:312

City:BAY POINT

State:CA

ZIP:94565-3299

Country:US

Phone:202-483-7616

CAGE:33564

=====
Composition/Information on Ingredients
=====

Ingred Name:EPOXY RESIN

Fraction by Wt: 57%

Ingred Name:FILLER

Fraction by Wt: 29%

Ingred Name:ASBESTOS (AMIANTHUS, OBSOLETE AMOSITE), (FOR OSHA PEL, SEE

29CFR 1910.1101)
CAS:1332-21-4
RTECS #:CI6475000
Fraction by Wt: 14%
OSHA PEL:0.2 FIBERS/CC
ACGIH TLV:0.5 FIBERS/CC; A1;89
EPA Rpt Qty:1 LB
DOT Rpt Qty:1 LB

=====
Hazards Identification
=====

Effects of Overexposure:CAUTION: MAY CAUSE SKIN AND EYE IRRITATIONS.

=====
First Aid Measures
=====

First Aid:WASH SKIN WITH SOAP AND WATER.FLUSH EYES IMMEDIATELY WITH
PLENTY OF WATER.

=====
Fire Fighting Measures
=====

Flash Point:>200 FTCC >93C
Extinguishing Media:CO*2,FOAM,DRY CHEMICALS
Fire Fighting Procedures:NONE
Unusual Fire/Explosion Hazard:NONE

=====
Accidental Release Measures
=====

Spill Release Procedures:REMOVE EXCESS.CLEAN RESIDUE WITH SOLVENTS.

=====
Handling and Storage
=====

Handling and Storage Precautions:STORE AT 77F
Other Precautions:READ CONTAINER LABELS.

=====
Exposure Controls/Personal Protection
=====

Respiratory Protection:APPROVED NIOSH RESPIRATOR AND MASK FOR ASBESTOS*
Ventilation:HIGHLY RECOMMENDED LOCAL EXHAUST AND MECHANICAL.
Eye Protection:SAFETY GLASSES OR GOGGLES
Other Protective Equipment:*THIS IS NOT NECESSARY UNLESS THE CURED
ADHESIVE IS "DRY SAN
Supplemental Safety and Health
PROCURED UNDER EA 901 PART A *IF IT IS NECESSARY TO SAND THE CURED
ADHESIVE #WET SANDING" IS RECOMMENDED TO ELIM. AIRBORNE ABESTOS FOR
"DRY SANDING" FILLLOW RECOMMEND

===== Physical/Chemical Properties =====

HCC:T6

Boiling Pt:B.P. Text:DECOMPOSES

Spec Gravity:1.52

Solubility in Water:NEGLIGIBLE

Appearance and Odor:VISCOUS, GREY PASTE WITH EPOXY ODOR

===== Stability and Reactivity Data =====

Stability Indicator/Materials to Avoid:YES

STRONG OXIDIZING AGENTS

Hazardous Decomposition Products:CARBON MONOXIDE,ALDEHYDES,ACIDS

Conditions to Avoid Polymerization:EXOTHERMS WHEN CURI

NG AGENTS ARE

ADDED.

===== Disposal Considerations =====

Waste Disposal Methods:LANDFILL OR CONTROLLED BURNING AS REGULATED BY
ALL GOVERNMENT AL AGENCIES.

Disclaimer (provided with this information by the compiling agencies):

This information is formulated for use by elements of the Department
of Defense. The United States of America in no manner whatsoever,
expressly or implied, warrants this information to be accurate and
disclaims all liability

for its use. Any person utilizing this
document should seek competent professional advice to verify and
assume responsibility for the suitability of this information to their
particular situation.