

FARWEST PAINT MFG CO -- 660 FLOOR & TRIM VARNISH -- 8010-00-165-4420

=====
Product Identification
=====

Product ID:660 FLOOR & TRIM VARNISH

MSDS Date:02/01/1993

FSC:8010

NIIN:00-165-4420

MSDS Number: BXGXP

=== Responsible Party ===

Company Name:FARWEST PAINT MFG CO

Address:4522 S 133 ST

City:TUKWILA

State:WA

ZIP:98168

Country:US

Info Phone Num:206-244-8844

Emergency Phone Num:206-941-1619

Prepare

r's Name:NORMA HABEEB

CAGE:6F266

=== Contractor Identification ===

Company Name:FARWEST PAINT MANUFACTURING CO

Address:4522 SOUTH 133RD ST

Box:City:TUKWILA

State:WA

ZIP:98168

Country:US

Phone:206-244-8844

CAGE:6F266

=====
Composition/Information on Ingredients
=====

Ingred Name:PETROLEUM SOLVENT

CAS:64742-47-8

Fraction by Wt: 5.61%

Other REC Limits:NONE RECOMMENDED

OSHA PEL:100 PPM

ACGIH TLV:100 PPM

Ingred Name:MINERAL SPIRITS 350

CAS:64475-85-0

RTECS #:PY8240000

Fraction by

Wt: 53.61%
Other REC Limits:NONE RECOMMENDED
OSHA PEL:100 PPM
ACGIH TLV:100 PPM

Ingred Name:XYLENE (SARA 313) (CERCLA)
CAS:1330-20-7
RTECS #:ZE2100000
Fraction by Wt: 0.10%
Other REC Limits:NONE RECOMMENDED
OSHA PEL:100 PPM
ACGIH TLV:100 PPM
EPA Rpt Qty:1000 LBS
DOT Rpt Qty:1000 LBS

Ingred Name:PHENYL ETHANE
CAS:100-41-4
RTECS #:DA0700000
Fraction by Wt: 0.03%
Other REC Limits:NONE RECOMMENDED
OSHA PEL:100 PPM
ACGIH TLV:100 PPM
EPA Rpt Qty:1000 LBS
DOT Rpt Qty:1000 LBS

Ingred Name:VOC: 530 G
RAMS/LITER (LESS WATER)
RTECS #:9999999VO
Other REC Limits:NONE RECOMMENDED

===== Fire Fighting Measures =====

Flash Point Method:TCC
Flash Point:103F,39C
Lower Limits:1.0
Upper Limits:7.0
Extinguishing Media:FOAM,DRY CHEM,WATER FOG,CO2.USE CLASS B
EXTINGUISHING AGENT.WATER UNSUITABLE AS EXTINGUISHING MEDIUM,USE TO
COOL CNTNRS.
Fire Fighting Procedures:FIREFIGHTERS & OTHERS EXPOSED TO VAPORS OR
COMBUSTION PRODUCTS WEAR SCBA. EVACUATE AREA OF UNPROT

ECTED

PERSONNEL. WEAR PROTECTIVE CLOTHING.

Unusual Fire/Explosion Hazard:VAPORS MAY FORM EXPLOSIVE MIX IN AIR & MAY BE IGNITED BY SPARKS, PILOT LIGHTS, ETC. CLOSED CONTAINRS MAY RUPTURE WHEN EXPOSED TO EXTREME HEAT.

=====
===== Exposure Controls/Personal Protection =====

Supplemental Safety and Health

=====
===== Physical/Chemical Properties =====

HCC:F4

Boiling Pt:B.P. Text:282 TO 387F

Vapor Pres:6.0 @ 68F

Vapor Density:> AIR

Evaporation Rate &a

mp; Reference:SLOWER THAN ETHER

Solubility in Water:NIL

Appearance and Odor:CLEAR LIQUID, MILD ODOR

Percent Volatiles by Volume:63

=====
===== Stability and Reactivity Data =====

Stability Indicator/Materials to Avoid:YES

AVOID CONTACT WITH STRONG OXIDANTS, ACIDS, BASES AND EPOXY HARDENERS UNDER UNCONTROLLED CONDITIONS.

Stability Condition to Avoid:HEAT, SPARKS, AND OPEN FLAMES. IF PRODUCT CONTAINS ALUMINUM, MOISTURE IN CLOSED CONTAINERS WILL GENERATE HYDROGEN G

AS.

Disclaimer (provided with this information by the compiling agencies):

This information is formulated for use by elements of the Department of Defense. The United States of America in no manner whatsoever, expressly or implied, warrants this information to be accurate and disclaims all liability for its use. Any person utilizing this document should seek competent professional advice to verify and assume responsibility for the suitability of this information to their particular si

tuation.