

PRATTVILLE BUILDERS INC -- PRIMER COATING: EPOXYCHEMICAL/SOLVENT RES 724226 02 --
8010-01-050-4082

===== Product Identification =====

Product ID:PRIMER COATING: EPOXYCHEMICAL/SOLVENT RES 724226 02

MSDS Date:03/03/1995

FSC:8010

NIIN:01-050-4082

Kit Part:Y

MSDS Number: CDJRS

=== Responsible Party ===

Company Name:PRATTVILLE BUILDERS INC

Address:474 E MAIN ST

Box:2153

City:PRATTVILLE

State:AL

ZIP:36

067

Country:US

Info Phone Num:205-365-2396/2145/312-455-2662NIGHT

Emergency Phone Num:205-365-2396/2145/312-455-2662NIGHT

Preparer's Name:W A ELLISON

CAGE:0EAH4

=== Contractor Identification ===

Company Name:PRATT AND LAMBERT INC

Box:6027

City:CLEVELAND

State:OH

ZIP:44101-1027

Country:US

Phone:216-566-2902

CAGE:61196

Company Name:PRATTVILLE BUILDERS INC

Address:474 E MAIN ST

Box:2153

City:PRATTVILLE

State:AL

ZIP:36067

Country:US

Phone:205-365-2396/2145/312-455-2662NIGHT

CAGE:0EAH4

=====

Composition/Information on Ingredients =====

Ingred Name:TOLUENE (SOLVENT) (SARA III) (CERCLA) (VAPOR PRESSURE 22 MM
HG @ 20C) (LFL 1.7; UFL 7.1) (SKIN)

CAS:108-88-3

RTECS #:XS5250000

Fraction by Wt: 20%

Other REC Limits:NONE RECOMMENDED

OSHA PEL:100 PPM;STEL 150 PPM

ACGIH TLV:50 PPM; 147 MG/M3

EPA Rpt Qty:1000 LBS

DOT Rpt Qty:1000 LBS

Ingred Name:DIGLYCIDYL ETHER OF BISPHENOL-A RESIN (RESIN)

CAS:25068-38-6

RTECS #:KC2100000

Fraction by Wt: 20%

Other REC Limits:NONE RECOMMENDED

Ingred Name:XYLENE (SOLVENT) (SARA 313) (CERCLA) (VAPOR PRESSURE 5 MM
HG @ 20C) (LFL 1.0; UFL 7.0)

CAS:1330-20-7

RTECS #:ZE2100000

Fraction by Wt: 5%

Other REC Limits:NONE RECOMMENDED

OSHA PEL:100 PPM;STEL 150 PPM

ACGIH TLV:100 PPM;STEL 150 PPM

EPA Rpt Qty:1000 LBS

DOT Rpt Qty:1000 LBS

Ingred Name:CARBON BLACK (PIGMENT)

CAS:1333-86-4

RTECS #:FF5800000

Fraction by Wt: